

CartonMate® C2S-HC Bleached Board

Reliability. It's that simple.®

Qualities:

- Smooth, bright appearance for excellent printability
- Heavy backside coating for increased barrier and sealing performance
- Consistent roll-to-roll quality
- FDA-compliant for contact with most dry, fatty and aqueous foods

Environmental attributes of RockTenn Bleached Board:

- SFI® Certified Participant
- Produced relying heavily on carbon-neutral biomass fuels as an energy source and ECF manufacturing techniques
- Bleached Board is recyclable* and derived from trees – a growing and renewable resource

*Packaging may not be recyclable in your area.

Typical Properties

| Caliper | .014 | .015 | .016 | .017 | .018 | .020 | .022 | .024 |
|----------------------|-------|-------|-------|-------|-------|-------|-------|-------|
| Nominal Basis Weight | 57.5 | 60.5 | 63.5 | 67.5 | 69.5 | 75.5 | 80.5 | 86.5 |
| Apparent Density | 12.32 | 12.10 | 11.91 | 11.91 | 11.58 | 11.32 | 10.98 | 10.81 |
| Taber Stiffness | | | | | | | | |
| MD | 130 | 155 | 180 | 210 | 245 | 315 | 395 | 495 |
| CD | 60 | 70 | 80 | 95 | 110 | 145 | 185 | 230 |
| GM | 88 | 104 | 120 | 141 | 165 | 214 | 270 | 337 |
| GE Brightness | 86 | 86 | 86 | 86 | 86 | 86 | 86 | 86 |
| Color Hunter b Value | 2.0 | 2.0 | 2.0 | 2.0 | 2.0 | 2.0 | 2.0 | 2.0 |
| Sheffield Smoothness | 20 | 22 | 24 | 26 | 28 | 32 | 36 | 40 |
| ZDT | 44 | 42 | 42 | 40 | 40 | 39 | 39 | 38 |
| Percent Moisture | 6.0 | 6.0 | 6.0 | 6.0 | 6.0 | 6.0 | 6.0 | 6.0 |

The information provided here identifies the target value for each product. The actual value of the characteristics may vary slightly from one run to another. This information is subject to change without notice.

CartonMate C2S-HC Bleached Board is produced at our Demopolis Mill in Demopolis, AL.

Contact Us:

www.rocktenn.com
877.643.5414



*Good for you.
Good for our forests.™*